

---

---

**Friction stir welding — Aluminium —  
Part 5:  
Quality and inspection requirements**

*Soudage par friction-malaxage — Aluminium —  
Partie 5: Exigences de qualité et de contrôle*

STANDARDSISO.COM : Click to view the full PDF of ISO 25239-5:2011



STANDARDSISO.COM : Click to view the full PDF of ISO 25239-5:2011



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

Page

Foreword .....	iv
Introduction.....	v
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions .....	2
4 Quality requirements.....	2
4.1 General .....	2
4.2 Welding personnel .....	2
4.3 Inspection and testing personnel .....	2
4.4 Equipment .....	2
4.5 Welding procedure specification.....	3
4.6 Friction stir welding tool.....	4
4.7 Preweld joint preparation and fit-up.....	4
4.8 Preheating and interpass temperature control .....	4
4.9 Tack welds .....	4
4.10 Welding.....	4
4.11 Postweld heat treatment.....	4
4.12 Inspection and testing .....	4
4.13 Identification and traceability.....	6
Annex A (normative) Imperfections, testing and examination, acceptance levels, and ISO 6520-1 reference number .....	7
Bibliography.....	9

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 25239-5 was prepared by the International Institute of Welding, which has been approved as an international standardizing body in the field of welding by the ISO Council.

ISO 25239 consists of the following parts, under the general title *Friction stir welding — Aluminium*:

- *Part 1: Vocabulary*
- *Part 2: Design of weld joints*
- *Part 3: Qualification of welding operators*
- *Part 4: Specification and qualification of welding procedures*
- *Part 5: Quality and inspection requirements*

Requests for official interpretations of any aspect of this part of ISO 25239 should be directed to the ISO Central Secretariat, who will forward them to the IIW Secretariat for an official response.

## Introduction

Welding processes are widely used in the fabrication of engineered structures. During the second half of the twentieth century, fusion welding processes, wherein fusion is obtained by the melting of parent material and usually a filler metal, dominated the welding of large structures. Then, in 1991, Wayne Thomas at TWI invented friction stir welding (FSW), which is carried out entirely in the solid phase (no melting).

The increasing use of FSW has created the need for this International Standard in order to ensure that welding is carried out in the most effective way and that appropriate control is exercised over all aspects of the operation. This International Standard focuses on the FSW of aluminium because, at the time of publication, the majority of commercial applications for FSW involved aluminium. Examples include railway carriages, consumer products, food processing equipment, aerospace structures, and marine vessels.

The parts of this International Standard are listed in the foreword.

Part 1 defines terms specific to FSW.

Part 2 specifies design requirements for friction stir weld joints in aluminium.

Part 3 specifies requirements for the qualification of an operator for the FSW of aluminium.

Part 4 specifies requirements for the specification and qualification of welding procedures for the FSW of aluminium. A welding procedure specification (WPS) is needed to provide a basis for planning welding operations and for quality control during welding. Welding is considered a special process in the terminology of standards for quality systems. Standards for quality systems usually require that special processes be carried out in accordance with written procedure specifications. Metallurgical deviations constitute a special problem. Because non-destructive testing of the mechanical properties is impossible at the present level of technology, this has resulted in the establishment of a set of rules for qualification of the welding procedure prior to the release of the WPS to actual production. ISO 25239-4 defines these rules.

Part 5 specifies a method for determining the capability of a manufacturer to use the FSW process for the production of aluminium products of the specified quality. It defines specific quality requirements but does not assign those requirements to any specific product group. To be effective, welded structures should be free from serious problems in production and in service. To achieve that goal, it is necessary to provide controls from the design phase through material selection, fabrication, and inspection. For example, poor design can create serious and costly difficulties in the workshop, on site, or in service. Incorrect material selection can result in welding problems, such as cracking. Welding procedures have to be correctly formulated and qualified to avoid imperfections. To ensure the fabrication of a quality product, management should understand the sources of potential trouble and introduce appropriate quality and inspection procedures. Supervision should be implemented to ensure that the specified quality is achieved.

STANDARDSISO.COM : Click to view the full PDF of ISO 25239-5:2017

# Friction stir welding — Aluminium —

## Part 5: Quality and inspection requirements

### 1 Scope

This part of ISO 25239 specifies a method for determining the capability of a manufacturer to use the friction stir welding (FSW) process for the production of products of the specified quality. It specifies quality requirements, but does not assign those requirements to any specific product group.

In this part of ISO 25239, the term “aluminium” refers to aluminium and its alloys.

This part of ISO 25239 does not apply to friction stir spot welding.

### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3452-1, *Non-destructive testing — Penetrant testing — Part 1: General principles*

ISO 4136, *Destructive tests on welds in metallic materials — Transverse tensile test*

ISO 5173, *Destructive tests on welds in metallic materials — Bend tests*

ISO 9015-1, *Destructive tests on welds in metallic materials — Hardness testing — Part 1: Hardness test on arc welded joints*

ISO 9015-2, *Destructive tests on welds in metallic materials — Hardness testing — Part 2: Microhardness testing of welded joints*

ISO 9017, *Destructive tests on welds in metallic materials — Fracture test*

ISO 9712, *Non-destructive testing — Qualification and certification of NDT personnel — General principles*

ISO 17636 (all parts), *Non-destructive testing of welds — Radiographic testing*<sup>1)</sup>

ISO 17637, *Non-destructive testing of welds — Visual testing of fusion-welded joints*

ISO 17640, *Non-destructive testing of welds — Ultrasonic testing — Techniques, testing levels, and assessment*

ISO 20807, *Non-destructive testing — Qualification of personnel for limited application of non-destructive testing*

ISO 25239-1, *Friction stir welding — Aluminium — Part 1: Vocabulary*

1) To be published. (Revision of ISO 17636:2003)

ISO 25239-3, *Friction stir welding — Aluminium — Part 3: Qualification of welding operators*

ISO 25239-4:2011, *Friction stir welding — Aluminium — Part 4: Specification and qualification of welding procedures*

### **3 Terms and definitions**

For the purposes of this document, the terms and definitions given in ISO 25239-1 apply.

### **4 Quality requirements**

#### **4.1 General**

These requirements relate only to those aspects of product quality that may be influenced by FSW.

#### **4.2 Welding personnel**

##### **4.2.1 General**

Manufacturers shall have at their disposal sufficient competent personnel for the planning, performance and supervision of FSW production operations in accordance with specified requirements.

##### **4.2.2 Welding operator**

Welding operators shall be qualified in accordance with ISO 25239-3. Qualification records shall be kept up to date.

#### **4.3 Inspection and testing personnel**

##### **4.3.1 General**

Manufacturers shall have sufficient competent personnel for the planning, performance, and supervision of inspection and testing operations during the production of friction stir welded parts in accordance with specified requirements.

##### **4.3.2 Personnel performing non-destructive testing and visual testing**

Non-destructive and visual testing personnel shall be qualified in accordance with ISO 9712 or ISO 20807. When the use of an examination method not currently incorporated in ISO 9712 or ISO 20807 is specified, the manufacturer shall be responsible for developing the training programme, written practice, examination, and practical demonstrations equivalent to the requirements of ISO 9712 or ISO 20807. These shall establish the capability of the personnel performing the required examination.

##### **4.3.3 Destructive testing personnel**

Personnel performing destructive testing shall be trained for those test methods.

#### **4.4 Equipment**

##### **4.4.1 Suitability of equipment**

The equipment shall be adequate for the application concerned.

Welding equipment (e.g. welding machines and FSW tools) shall be capable of producing welds that meet the acceptance levels specified in Annex A. Welding equipment shall be maintained in good condition and shall be repaired or adjusted when a welding operator, inspector or welding coordinator is concerned about the capability of the equipment to operate satisfactorily.

#### 4.4.2 New equipment

After installation of new or refurbished equipment, appropriate tests shall be performed. Such tests shall verify the equipment functions correctly.

#### 4.4.3 Reproducibility tests for qualified machine welding settings

Reproducibility tests shall be performed to demonstrate that the welding equipment can repeatedly produce welds that meet the acceptance levels in Annex A. Reproducibility tests shall be carried out when any of the following occurs:

- a critical component of the equipment is damaged, repaired, or replaced;
- equipment is dislodged or moved in a manner for which it was not designed;
- stationary equipment is moved from one location to another.

The reproducibility test shall be performed in accordance with a WPS that is used in production for that machine.

A minimum of three test welds shall be made and found satisfactory.

#### 4.4.4 Equipment maintenance

The manufacturer shall have a documented plan for equipment maintenance. The plan shall ensure that maintenance checks are performed on the equipment that controls variables listed in the relevant WPSs. The maintenance plan may be limited to those items that are essential for producing welds that meet the quality requirements of this part of ISO 25239.

Examples of these items are as follows:

- condition of guides and mechanized fixtures;
- condition of meters and gauges that are used for the operation of the welding equipment;
- condition of cables, hoses, and connectors;
- condition of the control systems in mechanized or automatic welding equipment;
- condition of thermocouples and other temperature measurement instruments;
- condition of clamps, jigs, and fixtures.

Before welding, clamps, jigs, and fixtures that contact the workpieces shall be clean and sufficiently free of contaminants (e.g. oil, grease, and dirt) that could have a detrimental effect on the weld.

Defective equipment shall not be used.

#### 4.5 Welding procedure specification

The manufacturer shall ensure the WPS is used correctly in production.

## 4.6 Friction stir welding tool

### 4.6.1 Identification

The FSW tool that is used in production shall be permanently marked for identification prior to use.

### 4.6.2 Friction stir welding tool inspection

Before welding, the FSW tool shall be clean and sufficiently free of contaminants (e.g. oil, grease or dirt) that could have a detrimental effect on weld quality. The correct tool geometry is critical for producing a quality friction stir weld. Because the FSW tool wears with use, it shall be inspected for wear at appropriate intervals and in accordance with a written procedure.

## 4.7 Preweld joint preparation and fit-up

### 4.7.1 Joint preparation

The edge of each joint member shall be prepared in accordance with the WPS.

The root gap shall be set in accordance with the WPS.

### 4.7.2 Preweld cleaning

Preweld cleaning shall be carried out in accordance with the WPS. Parent material shall be sufficiently free of surface oxides, protective finishes, adhesives, oils, grease, dirt, and any other contaminants that could have a detrimental effect on weld quality.

## 4.8 Preheating and interpass temperature control

Requirements for preheating and interpass temperature control shall be in accordance with a WPS.

## 4.9 Tack welds

If tack welds are required, they shall be made in accordance with a WPS.

## 4.10 Welding

All welding shall be done in accordance with a WPS.

## 4.11 Postweld heat treatment

If postweld heat treatment is required, it shall be done in accordance with a WPS.

The manufacturer shall be fully responsible for the specification and performance of any postweld heat treatment (e.g. solution heat-treating, stress relieving, or ageing). The procedure shall be compatible with the parent material, welded joint, and weldment, in accordance with the product standard or specified requirements. A record of the heat treatment shall be made during the heat-treating process. The record shall demonstrate that this part of ISO 25239 has been followed and shall be traceable to the heat-treated part.

## 4.12 Inspection and testing

### 4.12.1 General

The location and frequency of applicable inspections and tests depends on the product standard and the type of construction.

#### 4.12.2 Inspection and testing before welding

Before the start of welding, the following shall be verified:

- suitability and validity of the welding operator's qualification certificate;
- suitability of the WPS;
- parent material alloy and temper;
- joint preparation (e.g. shape and dimensions);
- joint fit-up, jiggling, and tacking;
- welding parameters set in accordance with the WPS;
- preheating and interpass temperature.

#### 4.12.3 Inspection and testing during welding

During welding, the welding sequence shall be checked at suitable intervals or by continuous monitoring.

#### 4.12.4 Inspection and testing after welding

##### 4.12.4.1 General

After welding, compliance with the relevant application standards or relevant requirements shall be verified for:

- visual testing;
- non-destructive testing;
- destructive testing;
- form, shape, and dimensions of the weldment;
- results and records of postweld operations (e.g. postweld heat treatment, ageing).

##### 4.12.4.2 Visual testing

Visual testing shall be performed in accordance with ISO 17637.

##### 4.12.4.3 Penetrant inspection

Penetrant inspection shall be performed in accordance with ISO 3452-1.

##### 4.12.4.4 Radiographic testing

Radiographic testing shall be performed in accordance with ISO 17636.

Ultrasonic examination may be used instead of radiographic testing when specified by the design specification or by relevant requirements.

When radiographic testing of lap joints or partial-penetration butt welds is required, the design specification shall determine the acceptance levels.

#### 4.12.4.5 Ultrasonic examination

Ultrasonic examination shall be performed in accordance with ISO 17640.

When immersion ultrasonic examination or phased-array ultrasonic examination is used, the design specification or relevant requirements shall determine the applicable standard(s) or requirements.

#### 4.12.4.6 Proof testing

Proof testing may be used in conjunction with, or in lieu of, the testing methods listed in 4.12.4.3 (penetrant), 4.12.4.4 (radiographic) and 4.12.4.5 (ultrasonic), when specified by the design specification or relevant requirements.

#### 4.12.4.7 Tensile testing

Tensile testing and the preparation of tensile test specimens shall be performed in accordance with ISO 4136.

#### 4.12.4.8 Bend testing

Bend testing and the preparation of bend test specimens shall be performed in accordance with ISO 5173.

For all parent materials, the minimum bend angle shall be 150° using the calculated former diameter based upon the parent material elongation as specified in ISO 25239-4:2011, 6.3.3.4.

#### 4.12.4.9 Hardness testing

Hardness testing shall be performed in accordance with ISO 9015-1 or ISO 9015-2, as applicable.

#### 4.12.4.10 Fracture testing

Fracture testing shall be performed in accordance with ISO 9017.

#### 4.12.4.11 Other destructive tests

Other destructive tests, procedures or techniques (e.g. impact tests, fatigue tests or macrographic and micrographic examination) not specifically addressed in this part of ISO 25239 may be used in conjunction with the tests stated herein. When one or more of these other testing methods is indicated, then they shall be carried out in accordance with the relevant International Standard.

#### 4.12.5 Damaged and non-conforming welds

If the repair of a damaged weld involves welding, then the repair shall be performed in accordance with a WPS. Repair shall bring the weld into full conformity with the requirements of this specification.

#### 4.12.6 Weld geometry correction

Toe flash or other protruding material along the edges of a friction stir weld and excess penetration may be removed by a method that does not degrade parent metal properties. This operation shall be carried out in such a manner that the thickness of the weld and parent material remain within tolerance.

#### 4.13 Identification and traceability

Identification and traceability of a weld to a WPS and welding operator or operators shall be maintained throughout the manufacturing process.