

NFPA 703
Standard for
Fire Retardant
Impregnated Wood
and Fire Retardant Coatings
for Building Materials

1995 Edition



National Fire Protection Association, 1 Batterymarch Park, PO Box 9101, Quincy, MA 02269-9101
An International Codes and Standards Organization

Copyright ©
National Fire Protection Association, Inc.
One Batterymarch Park
Quincy, Massachusetts 02269

IMPORTANT NOTICE ABOUT THIS DOCUMENT

NFPA codes and standards, of which the document contained herein is one, are developed through a consensus standards development process approved by the American National Standards Institute. This process brings together volunteers representing varied viewpoints and interests to achieve consensus on fire and other safety issues. While the NFPA administers the process and establishes rules to promote fairness in the development of consensus, it does not independently test, evaluate, or verify the accuracy of any information or the soundness of any judgments contained in its codes and standards.

The NFPA disclaims liability for any personal injury, property or other damages of any nature whatsoever, whether special, indirect, consequential or compensatory, directly or indirectly resulting from the publication, use of, or reliance on this document. The NFPA also makes no guaranty or warranty as to the accuracy or completeness of any information published herein.

In issuing and making this document available, the NFPA is not undertaking to render professional or other services for or on behalf of any person or entity. Nor is the NFPA undertaking to perform any duty owed by any person or entity to someone else. Anyone using this document should rely on his or her own independent judgment or, as appropriate, seek the advice of a competent professional in determining the exercise of reasonable care in any given circumstances.

The NFPA has no power, nor does it undertake, to police or enforce compliance with the contents of this document. Nor does the NFPA list, certify, test or inspect products, designs, or installations for compliance with this document. Any certification or other statement of compliance with the requirements of this document shall not be attributable to the NFPA and is solely the responsibility of the certifier or maker of the statement.

NOTICES

All questions or other communications relating to this document and all requests for information on NFPA procedures governing its codes and standards development process, including information on the procedures for requesting Formal Interpretations, for proposing Tentative Interim Amendments, and for proposing revisions to NFPA documents during regular revision cycles, should be sent to NFPA headquarters, addressed to the attention of the Secretary, Standards Council, National Fire Protection Association, 1 Batterymarch Park, P.O. Box 9101, Quincy, MA 02269-9101.

Users of this document should be aware that this document may be amended from time to time through the issuance of Tentative Interim Amendments, and that an official NFPA document at any point in time consists of the current edition of the document together with any Tentative Interim Amendments then in effect. In order to determine whether this document is the current edition and whether it has been amended through the issuance of Tentative Interim Amendments, consult appropriate NFPA publications such as the *National Fire Codes*[®] Subscription Service, visit the NFPA website at www.nfpa.org, or contact the NFPA at the address listed above.

A statement, written or oral, that is not processed in accordance with Section 16 of the Regulations Governing Committee Projects shall not be considered the official position of NFPA or any of its Committees and shall not be considered to be, nor be relied upon as, a Formal Interpretation.

The NFPA does not take any position with respect to the validity of any patent rights asserted in connection with any items which are mentioned in or are the subject of this document, and the NFPA disclaims liability of the infringement of any patent resulting from the use of or reliance on this document. Users of this document are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, is entirely their own responsibility.

Users of this document should consult applicable federal, state, and local laws and regulations. NFPA does not, by the publication of this document, intend to urge action that is not in compliance with applicable laws, and this document may not be construed as doing so.

Licensing Policy

This document is copyrighted by the National Fire Protection Association (NFPA). By making this document available for use and adoption by public authorities and others, the NFPA does not waive any rights in copyright to this document.

1. Adoption by Reference – Public authorities and others are urged to reference this document in laws, ordinances, regulations, administrative orders, or similar instruments. Any deletions, additions, and changes desired by the adopting authority must be noted separately. Those using this method are requested to notify the NFPA (Attention: Secretary, Standards Council) in writing of such use. The term “adoption by reference” means the citing of title and publishing information only.

2. Adoption by Transcription – **A.** Public authorities with lawmaking or rule-making powers only, upon written notice to the NFPA (Attention: Secretary, Standards Council), will be granted a royalty-free license to print and republish this document in whole or in part, with changes and additions, if any, noted separately, in laws, ordinances, regulations, administrative orders, or similar instruments having the force of law, provided that: (1) due notice of NFPA’s copyright is contained in each law and in each copy thereof; and (2) that such printing and republication is limited to numbers sufficient to satisfy the jurisdiction’s lawmaking or rule-making process. **B.** Once this NFPA Code or Standard has been adopted into law, all printings of this document by public authorities with lawmaking or rule-making powers or any other persons desiring to reproduce this document or its contents as adopted by the jurisdiction in whole or in part, in any form, upon written request to NFPA (Attention: Secretary, Standards Council), will be granted a nonexclusive license to print, republish, and vend this document in whole or in part, with changes and additions, if any, noted separately, provided that due notice of NFPA’s copyright is contained in each copy. Such license shall be granted only upon agreement to pay NFPA a royalty. This royalty is required to provide funds for the research and development necessary to continue the work of NFPA and its volunteers in continually updating and revising NFPA standards. Under certain circumstances, public authorities with lawmaking or rule-making powers may apply for and may receive a special royalty where the public interest will be served thereby.

3. Scope of License Grant – The terms and conditions set forth above do not extend to the index of this document.

(For further explanation, see the Policy Concerning the Adoption, Printing, and Publication of NFPA Documents, which is available upon request from the NFPA.)

Copyright © 1995 NFPA, All Rights Reserved

NFPA 703

Standard for

**Fire Retardant Impregnated Wood and
Fire Retardant Coatings for Building
Materials**

1995 Edition

This edition of NFPA 703, *Standard for Fire Retardant Impregnated Wood and Fire Retardant Coatings for Building Materials*, was prepared by the Technical Committee on Building Construction and acted on by the National Fire Protection Association, Inc., at its Annual Meeting held May 22-25, 1995, in Denver, CO. It was issued by the Standards Council on July 21, 1995, with an effective date of August 11, 1995, and supersedes all previous editions.

This edition of NFPA 703 was approved as an American National Standard on August 11, 1995.

Origin and Development of NFPA 703

In 1957, the Committee on Flameproofing and Preservative Treatments began to develop a standard for flameproofing of wood. It soon became clear to the committee that the fire retardant coating industry was expanding considerably, and that fire retardant admixtures of plastics and other building materials required coverage in the standard. Thus, in its many subsequent meetings, the Committee reexamined its approach and expanded the standard to cover all fire retardant treatments.

The standard was tentatively adopted at the 1960 Annual Meeting and was submitted for final adoption at the 1961 Annual Meeting.

The 1979 edition of NFPA 703, *Fire Retardant Impregnated Wood and Fire Retardant Coatings for Building Materials*, superseded the previous 1961 edition. The change in title was necessary to more adequately cover the subjects included in the text of the standard. The principal changes in the 1979 edition included improved definitions for fire retardant coatings.

The 1985 edition included the addition of a new Chapter 4 that listed referenced publications whose use is mandated within this standard.

In the 1992 edition, the Committee provided clarification in several areas defining fire resistance. The 1995 edition was reconfirmed with some editorial changes.

Technical Committee on Building Construction

Jack L. Kerin, *Chair*
State of California, CA

Rep. Nat'l Conference of States on Building Codes & Standards Inc.

Robert M. Berhinig, Underwriters Laboratories Inc., IL
Peter H. Billing, American Forest & Paper Assn., FL
William I. Blazek, U.S. General Services Administration, DC
John P. Chleapas, Framingham, MA
Richard J. Davis, Factory Mutual Research, MA
Alan J. Dopart, BRI Coverage Corp., NY
Elaine B. Gall, VA State Fire Marshal's Office, VA
Daniel F. Gemeny, Rolf Jensen & Assoc., Inc., CA
Richard G. Gewain, Hughes Assoc., Inc., MD
Karl D. Houser, Gypsum Assn., DC

Harlan C. Ihlenfeldt, Kemper Nat'l Insurance Cos., IL
Timothy J. Matey, Entergy Operations Inc., LA
Daniel M. McGee, American Iron & Steel Inst., NJ
Joseph J. Messersmith, Portland Cement Assn., VA
Brad Schiffer, Brad Schiffer/Taxis, Inc., FL
Raymond S. Szczucki, CIGNA Loss Control Services, PA
 Rep. American Insurance Services Group, Inc.
Lyndon Welch, Ann Arbor, MI
Peter J. Gore Willse, Industrial Risk Insurers, CT

Alternates

Kenneth E. Bland, American Forest & Paper Assn., NH
 (Alt. to P. H. Billing)
Donald J. Boehmer, Rolf Jensen & Assoc., Inc., IL
 (Alt. to D. F. Gemeny)
David W. Frable, U.S. General Services Administration, DC
 (Alt. to W. I. Blazek)

Todd E. Schumann, Industrial Risk Insurers, IL
 (Alt. to P. J. G. Willse)
Stephen V. Skalko, Portland Cement Assn., GA
 (Alt. to J. J. Messersmith)
Dean J. Tills, American Iron Steel Inst., DC
 (Alt. to D. M. McGee)

Steven F. Sawyer, NFPA Staff Liaison

This list represents the membership at the time the Committee was balloted on the text of this edition. Since that time, changes in the membership may have occurred.

NOTE: Membership on a committee shall not in and of itself constitute an endorsement of the Association or any document developed by the committee on which the member serves.

Committee Scope: This Committee shall have primary responsibility for documents on the design, installation and maintenance of building construction features not covered by other NFPA committees. (This Committee does not cover building code requirements, exits, protection at openings, vaults, air conditioning, blower systems, etc., which are handled by other committees.)

Contents

Chapter 1 General	703- 4	3-2 Definitions	703- 4
1-1 Scope	703- 4	3-3 General	703- 5
1-2 Definitions	703- 4	3-4 Tests	703- 5
Chapter 2 Fire Retardant Impregnated Wood	703- 4	3-5 Maintenance of Protection	703- 5
2-1 Application	703- 4	3-6 Identification	703- 5
2-2 Results of Treatment — All Species	703- 4	Chapter 4 Referenced Publications	703- 5
2-3 Tests	703- 4	Appendix A Explanatory Material	703- 5
2-4 Inspection and Identification	703- 4	Appendix B Referenced Publications	703- 5
2-5 Exposure	703- 4	Index	703- 7
Chapter 3 Fire Retardant Coatings for Building Materials	703- 4		
3-1 Application	703- 4		

NFPA 703

Standard for

Fire Retardant Impregnated Wood and Fire Retardant Coatings for Building Materials

1995 Edition

NOTICE: An asterisk (*) following the number or letter designating a paragraph indicates that explanatory material on the paragraph can be found in Appendix A.

Information on referenced publications can be found in Chapter 4 and Appendix B.

Chapter 1 General

1-1* Scope. This standard provides criteria for defining and identifying fire retardant impregnated wood and fire retardant coated building materials.

1-2 Definitions.

Authority Having Jurisdiction.* The organization, office, or individual responsible for approving equipment, an installation, or a procedure.

Labeled. Equipment or materials to which has been attached a label, symbol, or other identifying mark of an organization that is acceptable to the authority having jurisdiction and concerned with product evaluation that maintains periodic inspection of production of labeled equipment or materials and by whose labeling the manufacturer indicates compliance with appropriate standards or performance in a specified manner.

Chapter 2 Fire Retardant Impregnated Wood

2-1 Application. These requirements shall apply to pressure impregnation treatments that reduce certain burning characteristics of wood. Pressure impregnated lumber and plywood shall be treated for fire retardance in accordance with the requirements of the American Wood Preservers' Association Standard C1, *All Timber Product-Preservative Treatment by Pressure Process*, as modified herein. Other approved methods of impregnation of wood products providing at least equal performance shall also be considered acceptable.

2-2 Results of Treatment — All Species.

2-2.1 Conditions of Material.

2-2.1.1 Moisture Content. Subsequent to treatment, fire retardant treated lumber and plywood shall be air-dried or kiln-dried to an average moisture content of 19 percent or less for lumber and 15 percent or less for plywood in accordance with end-use requirements.

2-2.1.1.1 Air-Drying. Where material is air dried it shall not be exposed to conditions that could cause chemicals to leach out.

2-2.1.1.2 Kiln-Drying. During kiln-drying the dry bulb temperature of the kiln shall not exceed 16°F until the average moisture content of the wood has dropped to 25 percent or less.

2-2.2 Performance Rating.

2-2.2.1 Fire Hazard Classification. Material shall have a flame spread index of 25 or less with no evidence of significant progressive combustions when tested for 30 minutes by the test listed in Section 2-3. In addition, the flame front shall not progress more than 10.5 ft beyond the center line of the burner at any time during the test.

2-2.2.2 Interior Type A. Where experience demonstrates a specific need for the use of materials with low hygroscopicity, material shall have an equilibrium moisture content of not more than 28 percent when tested in accordance with the procedures in ASTM D3201, *Standard Test Method for Hygroscopic Properties of Fire-Retardant Wood and Wood-Base Products*, at 92 ± 2 percent relative humidity.

2-2.2.3 Interior Type B. Where experience demonstrates no specific need for the use of material with low hygroscopicity, the material shall have an equilibrium moisture content of not more than 28 percent when tested in accordance with the procedures in ASTM D3201, *Standard Test Method for Hygroscopic Properties of Fire-Retardant Wood and Wood-Base Products*, at 78 ± 2 percent relative humidity.

2-2.2.4 Exterior Type. Where material is to be used outdoors and subjected to rainfall or sustained humidity of 80 percent or more, the material shall show no increase in flame spread index when subjected to the standard rain test described in ASTM D2898, *Standard Methods for Accelerated Weathering of Fire Retardant-Treated Wood for Fire Testing — Method A*.

2-3* Tests. Fire retardant treated wood shall be tested in accordance with NFPA 255, *Standard Method of Test of Surface Burning Characteristics of Building Materials*.

2-4 Inspection and Identification. Inspection shall be required by an independent and qualified test agency that establishes the requirements for treatment relative to the preceding requirements. All fire retardant treated wood products shall be labeled by the testing agency certifying such ratings.

2-5 Exposure. Design criteria for fire retardant impregnated wood shall take into consideration the temperature and humidity conditions to which the material will be exposed.

Chapter 3 Fire Retardant Coatings for Building Materials

3-1 Application. These requirements shall apply to fire retardant coatings such as paints and other surface coatings used to reduce certain burning characteristics of building materials.

3-2 Definitions.

Fire Retardant Coating. A coating that reduces the flame spread of Douglas Fir, and all other tested combustible surfaces to which it is applied, by at least 50 percent or to a flame spread classification value of 75 or less, whichever is the lesser value, and has a smoke developed rating not exceeding 200.

Class A Fire Retardant Coating. As applied to building materials, shall reduce the flame spread to 25 or less, and have a smoke developed rating not exceeding 200.

Class B Fire Retardant Coating. As applied to building materials, shall reduce the flame spread to greater than 25 but not more than 75, and have a smoke developed rating not exceeding 200.

3-3 General.

3-3.1 Fire retardant coatings shall remain stable and adhere to the material under all atmospheric conditions the material is exposed to.

3-3.2 A fire retardant coating shall not be used for unprotected outdoor installations unless labeled for such installations.

3-3.3 The classification of fire retardant coatings is applicable only when the coating is applied at the rates of coverage and to the type or kind of surfaces indicated on the test report when the coating is applied in accordance with the manufacturer's directions supplied with the container.

3-3.4 These coatings shall be applied in accordance with the manufacturer's direction.

3-3.5 The authority having jurisdiction might require that the application be certified by the applicator as being in conformance with the manufacturer's direction for application.

3-3.6 A fire retardant coating shall not be overcoated with any material unless both the fire retardant coating and the overcoat have been tested as a system and are found to meet the requirements of a fire retardant coating.

3-4 Tests.

3-4.1* Fire retardant coatings shall be tested by NFPA 255, *Standard Method of Test of Surface Burning Characteristics of Building Materials*.

3-4.2 Where fire retardant coatings are to be subjected to sustained humidity of 80 percent or more or exposure to the weather, certification by a testing laboratory must indicate that there is no increase in listed classification when subjected to the "Standard Rain Test" described in ASTM D2898, *Standard Methods for Accelerated Weathering of Fire Retardant-Treated Wood for Fire Testing*.

3-5 Maintenance of Protection. Fire retardant coatings shall possess the desired degree of permanency and shall be maintained to retain the effectiveness of the treatment under the service conditions encountered in actual use.

3-6 Identification. Each container of fire retardant coating material shall be labeled to indicate conformance with the preceding requirements and shall include the manufacturer's instructions for application.

Chapter 4 Referenced Publications

4-1 The following documents or portions thereof are referenced within this standard and shall be considered part of the requirements of this document. The edition indicated for each reference is the current edition as of the date of the NFPA issuance of this document.

4-1.1 NFPA Publication. National Fire Protection Association, 1 Batterymarch Park, P.O. Box 9101, Quincy, MA 02269-9101.

NFPA 255, *Standard Method of Test of Surface Burning Characteristics of Building Materials*, 1990 edition.

4-1.2 Other Publications.

4-1.2.1 ASTM Publications. American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM D2898, *Standard Methods for Accelerated Weathering of Fire Retardant-Treated Wood for Fire Testing*, 1981.

ASTM D3201, *Standard Test Method for Hygroscopic Properties of Fire-Retardant Wood and Wood-Base Products*, 1986.

4-1.2.2 AWWPA Publication. American Wood Preservers Association, P.O. Box 286, Woodstock, MD 21163-0286.

C-1, *All Timber Product-Preservative Treatment by Pressure Process*, 1991.

Appendix A Explanatory Material

This Appendix is not a part of the requirements of this NFPA document but is included for informational purposes only.

A-1-1 Fire resistance ratings measured on an hourly basis are not covered in this standard. To establish such ratings, tests should be made in accordance with NFPA 251, *Standard Methods of Tests of Fire Endurance of Building Construction and Materials*.

A-1-2 Authority Having Jurisdiction. The phrase "authority having jurisdiction" is used in NFPA documents in a broad manner since jurisdictions and "approval" agencies vary as do their responsibilities. Where public safety is primary, the "authority having jurisdiction" may be a federal, state, local or other regional department or individual such as a fire chief, fire marshal, chief of a fire prevention bureau, labor department, health department, building official, electrical inspector, or others having statutory authority. For insurance purposes, an insurance inspection department, rating bureau, or other insurance company representative may be the "authority having jurisdiction." In many circumstances the property owner or his designated agent assumes the role of the "authority having jurisdiction"; at government installations, the commanding officer or departmental official may be the "authority having jurisdiction."

A-2-3 Test methods similar to NFPA 255, *Test for Surface Burning Characteristics of Building Materials*, include UL 723, *Standard Method of Test of Surface Burning Characteristics of Building Materials*, and ASTM E84, *Standard Test Method for Surface Burning Characteristics of Building Materials*. Under the criteria of NFPA 255, the flame spread rating is expressed numerically on a scale for which the zero point is fixed by the performance of inorganic-reinforced cement board and the 100 point (approximately) is fixed by the performance of untreated red oak flooring.

A-3-4.1 The flame spread rating is expressed numerically on a scale for which the zero point is fixed by the performance of inorganic-reinforced cement board and the 100 point (approximately) is fixed by the performance of red oak flooring.

Appendix B Referenced Publications

B-1 The following documents or portions thereof are referenced within this standard for informational purposes only and thus should not be considered part of the requirements

of this document. The edition indicated for each reference is the current edition as of the date of the NFPA issuance of this document.

B-1.1 NFPA Publication. National Fire Protection Association, 1 Batterymarch Park, P.O. Box 9101, Quincy, MA 02269-9101.

NFPA 251, *Standard Methods of Tests of Fire Endurance of Building Construction and Materials*, 1995 edition.

B-1.2 Other Publications.

B-1.2.1 UL Publication. Underwriters Laboratories Inc., 333 Pfingsten Road, Northbrook, IL 60062.

UL 723, *Test for Surface Burning Characteristics of Building Materials*, 7th edition.

B-1.2.2 ASTM Publication. American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E84, *Standard Test Method for Surface Burning Characteristics of Building Materials*, 1990.