



400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

# AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

AMS 3731/8A

Issued 10-1-81

Revised 10-1-87

Superseding AMS 3731/8

POTTING COMPOUND, EPOXY  
Bisphenol A-Type  
Filled, Heat Cure, High HDT

## 1. SCOPE:

1.1 Form: This specification covers an epoxy resin formulation supplied as a two-component system, requiring an oven cure for attainment of maximum properties.

1.2 Application: Primarily for use as a potting or sealing material where a high heat deflection temperature (HDT) is desired.

## 2. APPLICABLE DOCUMENTS: See AMS 3731.

## 3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3731.

3.2 Material: Shall be an epoxy-based polymer with a filler and a curing agent.

3.3 Properties: The compound shall conform to the following requirements:

3.3.1 Mixed Uncured Compound: The compound, mixed in accordance with manufacturer's instructions, shall exhibit the following properties:

3.3.1.1 Viscosity: Shall be not greater than 5000 centipoise (5.0 Pa·s) at 23°C (73°F), determined within 5 min. after mixing, using a Brookfield Model LVF viscometer and No. 3 spindle at 6 revolutions per minute.

3.3.1.2 Pot Life: Usable life of the compound, defined as the time to attain double the initial viscosity determined in 3.3.1.1, shall be not less than 30 min. at 23°C (73°F).

REAFFIRMED

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user." 10/91

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

3.3.1.3 Curing Time: The time required to develop the cured product properties specified in 3.3.2 shall be not more than 3 hr at 95°C (200°F) followed by not more than 16 hr at 205°C (400°F) or not more than 16 hr at 205°C (400°F).

3.3.2 Cured Product: The compound, mixed and cured in accordance with manufacturer's instructions, shall exhibit the following properties, determined in accordance with test methods listed in AMS 3731:

3.3.2.1	Flexural Strength, min	10,000 psi (70 MPa)
3.3.2.2	Izod Impact Strength, per unit of notch, min	0.28 ft-lb per in. (15 J/m)
3.3.2.3	Compressive Strength, min	15,000 psi (105 MPa)
3.3.2.4	Insulation Resistance	
3.3.2.4.1	At 23°C (73°F), min	$1 \times 10^6$ megohms
3.3.2.4.2	At 120°C (250°F), min	$1 \times 10^6$ megohms
3.3.2.4.3	After hydrolytic stability conditioning, min	$1 \times 10^4$ megohms
3.3.2.5	Dielectric Constant at 1 KHz, max	4.0
3.3.2.6	Dissipation Factor at 1 KHz, max	0.03
3.3.2.7	Heat Deflection Temperature at 264 psi (1.8 MPa), min	150°C (300°F)
3.3.2.8	Coefficient of Linear Thermal Expansion, max	
3.3.2.8.1	From -54°C to +23°C (-65°F to +73°F)	$35 \times 10^{-6}$ mm/mm per deg C ( $20 \times 10^{-6}$ in./in. per deg F)
3.3.2.8.2	From 23°C to 74°C (73°F to 165°F)	$45 \times 10^{-6}$ mm/mm per deg C ( $25 \times 10^{-6}$ in./in. per deg F)
3.3.2.9	Water Absorption after 24 hr Immersion, max	0.1%
3.3.2.10	Specific Gravity, max	2.2
3.3.2.11	Flammability (extent of burning), max	1 in. (25 mm)