

AEROSPACE MATERIAL SPECIFICATION

Issued OCT 1983
Revised JUL 1993
Reaffirmed JAN 2006

Superseding AMS 3799/4A

Webbing, Tubular, Low Modulus Aramid 3-3/16 (81) Wide, 2250 (10,008) Breaking Strength

1. SCOPE:

1.1 Form:

This specification covers one width and one breaking strength of low modulus aramid tubular webbing.

1.2 Application:

See AMS 3799.

1.3 Classification:

3-3/16 inches (81 mm) wide low modulus aramid tubular webbing having 2250 pounds force (10,008 N) breaking strength.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

See AMS 3799.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: custsvc@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification:

The complete requirements for procuring the tubular webbing described herein shall consist of this document and the latest issue of the basic specification, AMS 3799.

3.2 Construction and Properties:

3.2.1 Yarn: Yarn used in weaving the webbing shall be low modulus aramid with a carbonization (char) temperature not lower than 355 °C (671 °F).

3.2.1.1 Denier and Filament Count: The yarn shall be 200 denier \pm 15 and shall consist of 100 filaments \pm 10.

3.2.1.2 Ply: The yarn shall be four ply.

3.2.1.3 Twist: The final ply of yarn shall be twisted 2.5 to 2.8 turns per inch (25.4 mm).

3.2.2 Webbing:

3.2.2.1 Weave: Shall be tubular, plain, one up and one down.

3.2.2.2 Color: Shall be FED-STD-595 Sage Green 1565. The color shall be obtained by use of melt spun solution dyed yarn.

3.2.2.3 Width: Shall be 3.19 inches \pm 0.06 (81.0 mm \pm 1.5).

3.2.2.4 Thickness: Shall not exceed 0.045 inch (1.14 mm).

3.2.2.5 Weight: Shall not exceed 1.85 ounces per linear yard (57.4 g/m).

3.2.2.6 Breaking Strength: Shall be not less than 2250 pounds force (10,008 N) unaged and not less than 85% of the unaged strength after aging.

3.2.2.7 Ultimate Elongation: Shall be not less than 12.0%.

3.2.2.8 Thread Count: Warp ends shall be not less than 309. Filling picks shall be not less than 60 per inch (25.4 mm).

3.3 Length of Put-up:

Webbing shall be furnished in rolls containing 160 yards \pm 10 (146 m \pm 9). Not more than two pieces shall be contained in any one roll.