

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE

AMS 4070K

Issued OCT 1940
Revised SEP 1995

Superseding AMS 4070J

ALUMINUM ALLOY, DRAWN, ROUND SEAMLESS TUBING
2.5Mg - 0.25Cr (5052-0)
Annealed

UNS A95052

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of drawn, round seamless tubing.

1.2 Application:

This tubing has been used typically for parts, such as brackets, conduits, and low-pressure fluid lines, requiring good weldability, moderate strength, and good resistance to corrosion, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings

MAM 2355 Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units

AMS 2811 Identification, Aluminum and Magnesium Alloy Wrought Products

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1995 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

AMS 4070K**SAE****AMS 4070K****2.2 ASTM Publications:**

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

2.3 ANSI Publications:

Available from American National Standards Institute, Inc., 11 West 42nd Street, New York, NY 10036-8002.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products

3. TECHNICAL REQUIREMENTS:**3.1 Composition:**

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition

Element	min	max
Magnesium	2.2	2.8
Chromium	0.15	0.35
Iron	--	0.40
Silicon	--	0.25
Zinc	--	0.10
Manganese	--	0.10
Copper	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

3.2 Condition:

Annealed.

3.3 Properties:

Tubing shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

- 3.3.1 Tensile Properties: Shall be as shown in Table 2 for tubing having nominal wall thickness of 0.010 to 0.450 inch (0.25 to 11.43 mm), inclusive.

AMS 4070K

SAE

AMS 4070K

TABLE 2 - Tensile Properties

Property	Value
Tensile Strength	25.0 to 35.0 ksi (172 to 241 MPa)
Yield Strength at 0.2% Offset, min	10.0 ksi (68.9 MPa)

3.3.2 Flattening: Tubing having nominal wall thickness less than 10% of the nominal OD shall withstand, without cracking, flattening sideways under a load applied gradually at room temperature until the outside dimension under load is equal to three times the nominal wall thickness.

3.3.2.1 If tubing does not pass the flattening test of 3.3.2, a section of tube not less than 1/2 inch (12.7 mm) in length and embracing one-third to one-half the circumference of the tube shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the nominal wall thickness of the tubing with axis of bend parallel to axis of tube and with inside of tube on inside of bend.

3.3.3 Flarability: Tubing with a nominal OD of 0.125 to 0.312 inch (3.18 to 7.92 mm) and wall thickness up to 0.035 inch (0.89 mm) and tubing with a nominal OD of 0.313 to 0.375 inch (7.95 to 9.52 mm) and nominal wall thickness not greater than 0.049 inch (1.24 mm) shall withstand double-flaring (See 8.2), and tubing with nominal OD over 0.375 inch (9.52 mm) shall withstand single-flaring without formation of cracks or other visible defects by being forced, at room temperature, axially with steady pressure over a hardened and polished tapered steel pin having a 74-degree included angle to produce a flare having a permanent expanded OD not less than specified in Table 2.

TABLE 2A - Minimum Flarability, Inch/Pound Units

Nominal OD Inch	Expanded OD Inch	Nominal OD Inches	Expanded OD Inches
0.125	0.200	1.000	1.187
0.188	0.302	1.250	1.500
0.250	0.359	1.500	1.721
0.312	0.421	1.750	2.106
0.375	0.484	2.000	2.356
0.500	0.656	2.500	2.856
0.625	0.781	3.000	3.356
0.750	0.937		

AMS 4070K

SAE

AMS 4070K

TABLE 2B - Minimum Flarability, SI Units

Nominal OD Millimeters	Expanded OD Millimeters	Nominal OD Millimeters	Expanded OD Millimeters
3.18	5.08	25.40	30.15
4.78	7.67	31.75	38.10
6.35	9.12	38.10	43.71
7.92	10.69	44.45	53.49
9.52	12.29	50.80	59.84
12.70	16.66	63.50	72.54
15.88	19.84	76.20	85.24
19.05	23.80		

3.3.3.1 Tubing with nominal OD between any two standard sizes shown in Table 2 shall take the same percentage flare as shown for the larger of the two sizes.

3.4 Quality:

Tubing, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the tubing.

3.5 Tolerances:

(R)

Shall conform to all applicable requirements of ANSI H35.2.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), tensile properties (3.3.1), and tolerances (3.5) are (R) acceptance tests and, except for composition, shall be performed on each inspection lot.

4.2.2 Periodic Tests: Flattening (3.3.2) and flarability (3.3.3) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2355 or MAM 2355 and the following: