



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 4140E

Superseding AMS 4140D

Issued	1-1-42
Revised	10-16-78

UNS A92018

ALUMINUM ALLOY FORGINGS
4.0Cu - 2.0Ni - 0.68Mg (2018-T61)

1. SCOPE:

- 1.1 Form: This specification covers an aluminum alloy in the form of die forgings and forging stock.
- 1.2 Application: Primarily for pistons for aircraft reciprocating engines. Certain design and processing procedures may cause this material to be susceptible to stress-corrosion cracking; ARP 823 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) and Aerospace Recommended Practices (ARP) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2201 - Tolerances, Aluminum and Aluminum Alloy Bar, Rod, Wire, and Forging Stock,
Rolled or Drawn
AMS 2350 - Standards and Test Methods
AMS 2375 - Control of Forgings Requiring First-Article Approval
AMS 2630 - Ultrasonic Inspection
AMS 2808 - Identification, Forgings

2.1.2 Aerospace Recommended Practices:

ARP 823 - Minimizing Stress Corrosion Cracking in Wrought Heat Treatable Aluminum Alloy Products

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B557 - Tension Testing Wrought- and Cast-Aluminum- and Magnesium-Alloy Products
ASTM E10 - Brinell Hardness of Metallic Materials
ASTM E34 - Chemical Analysis of Aluminum and Aluminum Alloys

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Specifications:

MIL-H-6088 - Heat Treatment of Aluminum Alloys

SAE Technical Board rules provide that: "All technical reports, including standards approved and published, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

2.3.3 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E34, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

	min	max
Copper	3.5	4.5
Nickel	1.7	2.3
Magnesium	0.45	0.9
Iron	--	1.0
Silicon	--	0.9
Zinc	--	0.25
Manganese	--	0.20
Chromium	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

- 3.2 Condition: The product shall be supplied in the following condition:

Ø 3.2.1 Forgings: Solution and precipitation heat treated in accordance with MIL-H-6088.

Ø 3.2.2 Forging Stock: As ordered by the forging manufacturer.

- 3.3 Properties: The product shall conform to the following requirements:

3.3.1 Forgings:

Ø 3.3.1.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM B557:

- 3.3.1.1.1 Test Specimens: Test specimens, machined from separately-forged coupons or from forging stock representing the forgings and, in either case, heat treated with the forgings or machined from prolongations on heat treated forgings, shall have the following properties:

Tensile Strength, min	55,000 psi (379 MPa)
Yield Strength at 0.2% Offset, min	40,000 psi (276 MPa)
Elongation in 4D, min	10%

- 3.3.1.1.2 Forgings With Grain Flow: Test specimens machined from forgings, with the axis of specimen in the area of gage length varying not more than 15 deg from parallel to the forging flow lines, shall have properties as specified in 3.3.1.1.1.

- 3.3.1.2 Hardness: Should be not lower than 100 HB/10/500, 100 HB/14.3/1000, or 106 HB/10/1000, determined in accordance with ASTM E10, but forgings shall not be rejected on the basis of hardness if the tensile property requirements are met. Piston forgings shall also meet the requirements of 3.3.1.2.1.
- Ø

3.3.1.2.1 Piston forgings shall retain hardness not lower than 90 HB/10/500, 90 HB/14.3/1000, or 93 HB/10/1000, determined in accordance with ASTM E10, after being heated to 450° F \pm 10 (230° C \pm 5), held at heat for 5 hr \pm 0.2, and cooled in air.

Ø 3.3.1.3 Grain Flow: Shall be as specified on the drawing or as agreed upon by purchaser and vendor.

3.3.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated in the same manner as forgings, specimens taken from the heat treated coupon shall conform to the requirements of 3.3.1.1.1 and 3.3.1.2. If specimens taken from the stock after heat treatment in the same manner as forgings conform to the requirements of 3.3.1.1.1 and 3.3.1.2, the tests shall be accepted as equivalent to tests of a forged coupon. The forging stock supplier, however, shall not be required to conduct such tests.

3.4 Quality: The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.

3.4.1 When specified, forgings shall be subjected to ultrasonic inspection in accordance with AMS 2630.
Ø Standards for acceptance shall be as agreed upon by purchaser and vendor.

3.5 Tolerances: Unless otherwise specified, tolerances for forging stock shall conform to all applicable requirements of AMS 2201.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests of the product to determine conformance to requirements for composition (3.1) and forgings to determine conformance to requirements for tensile properties (3.3.1.1), hardness (3.3.1.2), quality (3.4) and, when specified, ultrasonic inspection (3.4.1) are classified as acceptance tests and shall be performed on each lot of product.

4.2.2 Periodic Tests: Tests of forgings to determine conformance to requirements for grain flow (3.3.1.3) and, when applicable, hardness retention (3.3.1.2.1) and of forging stock to determine ability to develop required properties (3.3.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed on the first-article shipment of the product to a purchaser, when a change in material or processing requires reapproval, or when purchaser deems confirmation testing is required.

4.2.3.1 For direct U.S. Military procurement of forgings, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be as follows; a lot shall be all forgings of the same part number, size, or nominal cross-section and configuration heat treated in the same batch furnace load or in a continuous furnace consecutively during an 8-hr period.

4.3.1 Acceptance Tests:

4.3.1.1 Composition: At least one sample shall be taken by the producer from each group of ingots poured simultaneously from the same source of molten metal. Complete ingot analysis records shall be available to the purchaser at the producer's facility.

4.3.1.1.1 Unless compliance with 4.3.1.1 is established, an analysis shall be made for each 6000 lb (2724 kg) or less of material comprising the lot, except that not more than one analysis shall be required per piece.

4.3.1.2 Tensile Properties:

4.3.1.2.1 Forgings: At least one separately-forged coupon or one forging prolongation, heat treated with each lot of forgings.

4.3.1.2.1.1 In lieu of a prolongation or separately-forged coupon, tensile test specimens shall be cut from a forging representing each lot from locations designated on the drawing or as agreed upon by purchaser and vendor.

Ø 4.3.2 Periodic Tests and Preproduction Tests: As agreed upon by purchaser and vendor.

4.4 Approval: When specified, approval and control of forgings shall be in accordance with AMS 2375.

4.5 Reports:

4.5.1 The vendor of forgings shall furnish with each shipment three copies of a report stating that the chemical composition conforms to the requirements of this specification, showing the results of tests on each lot to determine conformance to the other acceptance test requirements, and stating that the forgings conform to the other technical requirements of this specification. This report shall include the purchase order number, lot number, material specification number and its revision letter, size or part number, and quantity.

4.5.2 The vendor of forging stock shall furnish with each shipment three copies of a report stating that the chemical composition of the stock conforms to the requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, size, and quantity.

4.5.3 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of forgings, part number and quantity. When forgings for making parts are produced or purchased by the parts vendor, that vendor shall inspect each lot of forgings to determine conformance to the requirements of this specification, and shall include in the report a statement that the forgings conform, or shall include copies of laboratory reports showing the results of tests to determine conformance.

4.6 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the product may be based on the results of testing two additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the product represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification: The product shall be identified as follows:

5.1.1 Forgings: In accordance with AMS 2808.

5.1.2 Forging Stock: As agreed upon by purchaser and vendor.