

UNS S92411

STEEL CASTINGS, SAND, CORROSION AND HEAT RESISTANT
24.5Cr - 20.5Ni
Solution Heat Treated

1. SCOPE:

1.1 Form: This specification covers a corrosion and heat resistant steel in the form of sand castings.

1.2 Application: Primarily for parts, such as nozzle diaphragm vanes, requiring both corrosion and heat resistance and which may be welded during fabrication. The steel is oxidation resistant up to 2000°F (1095°C) but is useful at the higher temperatures only when stresses are very low. Strength at elevated temperatures is similar to that of the 18Cr - 8Ni types.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2350 - Standards and Test Methods
- AMS 2360 - Room Temperature Tensile Properties of Castings
- AMS 2635 - Radiographic Inspection
- AMS 2645 - Fluorescent Penetrant Inspection
- AMS 2694 - Repair Welding of Aerospace Castings
- AMS 2804 - Identification, Castings

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade or their use by governmental agencies is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and other Similar Chromium-Nickel-Iron Alloys

ASTM E446 - Reference Radiographs for Steel Castings Up to 2 In. (51 mm) in Thickness

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	0.10	0.18
Manganese	--	2.00
Silicon	0.50	1.50
Phosphorus	--	0.04
Sulfur	--	0.04
Chromium	23.00	26.00
Nickel	19.00	22.00
Molybdenum	--	0.75
Copper	--	0.75

3.2 Condition: Solution heat treated.

3.3 Casting: A melt shall be the metal poured from a single furnace charge of \varnothing 10,000 lb (4500 kg) or less. A lot shall be all castings poured from a single melt in not more than 8 consecutive hours and heat treated together as a batch.

3.4 Test Specimens:

- 3.4.1 Chemical Analysis Specimens: Shall be of any convenient size, shape, and form for vendor's tests. When chemical analysis specimens are required by purchaser, specimens shall be cast to a size, shape, and form agreed upon by purchaser and vendor.
- 3.4.2 Tensile Specimens: Shall be attached to castings, if practicable, or shall be standard keel blocks conforming to ASTM A370, unless purchaser permits use of cast-to-size specimens. Specimens shall be cast with each melt of metal for castings and, when requested, shall be supplied with the castings. Keel blocks shall be cast in molds made of suitable core sand, shall be poured directly after pouring the castings, and shall be kept in the mold until black. Metal for the specimens shall be part of the melt which is used for the castings.
- 3.5 Heat Treatment: Castings and separately-cast tensile specimens shall be solution heat treated by heating to a temperature within the range 2025° - 2075°F (1110° - 1135°C), holding at the selected temperature within + 25°F (+15°C) for not less than 30 min., and cooling rapidly to room temperature.
- 3.6 Properties: Castings and separately-cast tensile specimens shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370:
- 3.6.1 Tensile Properties:
- 3.6.1.1 Separately-Cast, Attached, or Keel Block Specimens: Shall be as follows, determined on specimens produced as in 3.4.2 and heat treated as in 3.5:
- | | |
|------------------------------------|----------------------|
| Tensile Strength, min | 65,000 psi (450 MPa) |
| Yield Strength at 0.2% Offset, min | 28,000 psi (195 MPa) |
| Elongation in 4D, min | 30% |
- 3.6.1.2 Specimens Cut from Castings: Tensile specimens conforming to ASTM A370 shall be machined from castings selected at random from each melt in the shipment. Size, number, and location of such specimens and required properties shall be as shown on the drawing or as agreed upon by purchaser and vendor. Property requirements may be defined as specified in AMS 2360.
- 3.6.2 Hardness: Should be not higher than 170 HB or equivalent but castings shall not be rejected on the basis of hardness if the tensile property requirements are met.
- 3.7 Quality:
- 3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the castings.

3.7.1.1 Castings shall have smooth surfaces and shall be well cleaned. Metallic shot or grit shall not be used for final cleaning, unless otherwise permitted.

3.7.2 Castings shall be produced under radiographic control, unless otherwise specified. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.7.3 When specified, castings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645.

3.7.4 Radiographic, fluorescent penetrant, and other quality standards shall be
Ø as agreed upon by purchaser and vendor. ASTM E446 may be used to define radiographic acceptance standards.

3.7.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.

3.7.5.1 When permitted in writing by purchaser, defects in castings may be
Ø removed and the castings repaired by welding in accordance with AMS 2694.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all
Ø required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Except as specified in 4.2.1.1, tests to determine
Ø conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each melt or lot as applicable.

4.2.1.1 Tensile properties of specimens cut from castings shall be determined
Ø only when specified by purchaser or when attached or separately-cast specimens are not available. Tensile properties of attached or separately-cast specimens need not be determined when tensile properties of specimens cut from castings are determined.

4.2.2 Preproduction Tests: Tests to determine conformance to all technical
Ø requirements of this specification are classified as preproduction tests and shall be performed on the first-article shipment of a casting to a purchaser, when a change in material and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be in accordance with the following:

4.3.1 Two chemical analysis specimens in accordance with 3.4.1 from each melt and/or a casting from each lot.

4.3.2 Two preproduction castings in accordance with 4.4.1 of each part number.

4.3.3 Three tensile specimens in accordance with 3.4.2 from each melt, when requested.

4.3.4 One or more castings from each lot when properties of specimens machined from castings are required. Size, location, and number of specimens machined from castings shall be as specified on the drawing or as agreed upon by purchaser and vendor. When size, location, and number of specimens are not specified, not less than two tensile specimens, one from the thickest section and one from the thinnest section, shall be cut from a casting or castings from each lot.

4.4 Approval:

4.4.1 Sample castings from new or reworked patterns and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.

4.4.2 Vendor shall establish for production of sample castings of each part number parameters for the control factors of processing which will produce acceptable castings; these shall constitute the approved casting procedure and shall be used for producing production castings. If necessary to make any change in parameters for the control factors of processing, vendor shall submit for reapproval a statement of the proposed changes in processing and, when requested, sample test specimens, castings, or both. Production castings incorporating the revised operations shall not be shipped prior to receipt of reapproval.

4.4.2.1 Control factors for producing castings include, but are not limited to, the following:

- Type of furnace
- Furnace atmosphere
- Fluxing or deoxidation procedure
- Gating and risering practices
- Pouring temperature (variation of + 50°F (+ 30°C) from the established limit is permissible)
- Solidification and cooling procedures
- Solution heat treatment cycle
- Cleaning operations
- Methods of inspection