



# AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N.Y. 10017

AMS 5746A

Issued 6-30-60  
Revised 3-15-66

## ALLOY, CORROSION AND HEAT RESISTANT

15Cr - 45Ni - 4W - 4Mo - 3Ti - 1Al

Consumable Electrode Vacuum Melted

- ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
- FORM:** Bars, forgings, and stock for forging or heading.
- APPLICATION:** Primarily for parts such as turbine rotors, shafts, buckets or blades, bolts, dowels, and fittings requiring high strength up to 1600 F (871 C) and oxidation resistance up to 1800 F (982 C).
- COMPOSITION:**

	min	max
Carbon	--	0.08
Manganese	--	0.75
Silicon	--	0.75
Phosphorus	--	0.040
Sulfur	--	0.040
Chromium	14.00	16.00
Nickel	42.00	48.00
Molybdenum	3.00	4.50
Tungsten	3.00	4.50
Titanium	2.70	3.30
Aluminum	0.75	1.30
Boron	0.008	0.016
Iron	remainder	

- Check Analysis:** Composition variations shall meet the requirements of the latest issue of AMS 2248.

### 5. CONDITION:

- Bars and Forgings:** Solution and precipitation heat treated, unless otherwise specified.

- Stock for Forging or Heading:** As ordered by the forging or heading manufacturer.

### 6. TECHNICAL REQUIREMENTS:

#### 6.1 Bars and Forgings:

- Heat Treatment:** The product shall be solution heat treated by heating to 1900 F  $\pm$  25 (1037.8 C  $\pm$  14), holding at heat for 1 hr, and quenching in oil, and shall then be precipitation heat treated by heating to 1550 F  $\pm$  25 (843.3 C  $\pm$  14), holding at heat for 6 hr, air cooling, heating to 1300 F  $\pm$  25, holding at heat for 16 hr, and air cooling.

- Tensile Properties:** Tensile test specimens taken from bars and forgings and tested at room temperature shall conform to the following requirements:

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

6.1.2.1 Bars:

Tensile Strength, psi	190,000 min
Yield Strength at 0.2% Offset or at 0.0123 in. in 2 in. Extension Under Load ( $E = 30,000,000$ ), psi	125,000 min
Elongation, % in 4D Up to 0.75 in., incl, diameter, or equivalent cross-section	12 min
Over 0.75 in. diameter or equivalent cross-section	10 min
Reduction of Area, % Up to 3/4 in. Rd, incl, or equivalent cross-section	15 min
Over 3/4 in. Rd, or equivalent cross-section	12 min

6.1.2.2 Forgings:

Tensile Strength, psi	170,000 min
Yield Strength at 0.2% Offset or at 0.0123 in. in 2 in. Extension Under Load ( $E = 30,000,000$ ), psi	125,000 min
Elongation, % in 4D	8 min
Reduction of Area, %	10 min

6.1.2.3 When a dispute occurs between purchaser and vendor over the yield strength values, yield strength determined by the offset method shall apply.

6.1.3 Hardness: Shall be Brinell 340 - 418 or equivalent.

6.1.4 Stress-Rupture Test at 1200 F (648.9 C): A combination smooth and notched test specimen machined from bars and forgings to the dimensions shown in Fig. 1 and Table I, maintained at  $1200\text{ F} \pm 3$  ( $648.9\text{ C} \pm 1.7$ ) while an axial stress of 90,000 psi is applied continuously, shall not rupture in less than 23 hours. The test shall be continued to rupture, either maintaining the same stress or increasing the stress in 5000 psi increments after 48 hr and at intervals of not less than 8 hr thereafter. Rupture  $\emptyset$  shall occur in the smooth section and elongation of this section after rupture, measured at room temperature, shall be not less than 5% in 4D if the specimen ruptures in 48 hr or less, and not less than 3% in 4D if the specimen ruptures in more than 48 hours. Tests shall be conducted in accordance with the issue of ASTM E139 specified in the latest issue of AMS 2350.

6.1.4.1 As an alternate procedure, separate smooth and notched test specimens, machined from adjacent sections of the same piece, with gage sections conforming to the respective dimensions of Table I may be tested individually under the above conditions, including increase of stress after 48 hours. The smooth specimen shall not rupture in less than 23 hr and elongation after rupture, measured at room temperature, shall be as specified above. The notched specimen need not be tested to rupture but shall not rupture in less time than the companion smooth specimen.

6.2 Stock for Forging or Heading: When a sample of stock is forged to a test coupon as agreed upon by purchaser and vendor and heat treated as in 6.1.1, specimens taken from the heat treated coupon shall conform to the requirements of 6.1.2.2, 6.1.3, and 6.1.4. If specimens taken from the stock after heat treatment as in 6.1.1 conform to the requirements of 6.1.2.2, 6.1.3, and 6.1.4, the tests shall be accepted as equivalent to tests of the forged coupon.

7. QUALITY: Material shall be multiple melted using vacuum consumable electrode practice in the remelt cycle, unless otherwise specified. The product shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

8. TOLERANCES: Unless otherwise specified, tolerances for bars shall conform to all applicable requirements of the latest issue of AMS 2241.

9. REPORTS:

- 9.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each heat in the shipment and the results of tests on each size from each heat to determine conformance to the technical requirements of this specification. This report shall include the purchase order number, heat number, material specification number, size, and quantity from each heat. If forgings are supplied, the part number and size of stock used to make the forgings shall also be included.
- 9.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

10. IDENTIFICATION:

- 10.1 Bars: Individual pieces or bundles shall have attached a metal or plastic tag embossed with the purchase order number, AMS 5746A, nominal size, and heat number, or shall be boxed and the box marked with the same information. In addition to the above identification, flats 2 x 1 in. and larger and other bars 1 in. and over in diameter or distance between parallel sides shall be stamped with the heat number within 2 in. of one end.
- 10.2 Forgings: Shall be identified in accordance with the latest issue of AMS 2808.
- 10.3 Stock for Forging or Heading: Shall be identified as agreed upon by purchaser and vendor.

11. REJECTIONS: Material not conforming to this specification or to authorized modifications will be subject to rejection.

SAENORM.COM: Click to view the full PDF of ams5746a