

AEROSPACE MATERIAL SPECIFICATION



AMS5763

REV. D

Issued 1972-12
Reaffirmed 2006-04
Revised 2010-06

Superseding AMS5763C

Steel, Corrosion Resistant Bars, Forgings, Tubing, and Rings
15Cr - 6.5Ni - 0.75Mo - 0.50Cb (Nb) - 1.5Cu
Solution Heat Treated

(Composition similar to UNS S45000)

RATIONALE

AMS5763D revises Table 1 and Reports (4.4), and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion-resistant steel in the form of bars, wire, forgings, mechanical tubing, flash welded rings, and stock for forging or flash welded rings.

1.2 Application

These products have been used typically for parts requiring corrosion resistance approximating that of steels of the 18-8 types and high strength exceeding that of the 12 Cr martensitic types up to 700 °F (370 °C), but usage is not limited to such applications.

1.3 This steel can be used in the solution heat treated condition and is capable of being precipitation heat treated to tensile strengths as high as 180 ksi (1240 MPa).

1.4 Although this steel is relatively immune to stress-corrosion cracking, reference should be made to ARP1110 for recommended practices to minimize such conditions.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2010 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS5763D>**

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS2241	Tolerances, Corrosion and Heat-Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire
AMS2243	Tolerances, Corrosion and Heat-Resistant Steel Tubing
AMS2248	Chemical Check Analysis Limits, Corrosion and Heat-Resistant Steels and Alloys, Maraging and Other Highly-Alloyed Steels, and Iron Alloys
AMS2303	Steel Cleanliness, Aircraft Quality, Martensitic Corrosion-Resistant Steels, Magnetic Particle Inspection Procedure
AMS2371	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS2374	Quality Assurance Sampling and Testing, Corrosion and Heat-Resistant Steel and Alloy Forgings
AMS2750	Pyrometry
AMS2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat-Resistant Steels and Alloys
AMS2808	Identification, Forgings
AMS7490	Rings, Flash Welded, Corrosion and Heat-Resistant Austenitic Steels, Austenitic-Type Iron, Nickel, or Cobalt Alloys, or Precipitation-Hardenable Alloys
ARP1110	Minimizing Stress Corrosion Cracking in Wrought Forms of Steels and Corrosion Resistant Steels and Alloys

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM A 370	Mechanical Testing of Steel Products
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Carbon	--	0.05
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.030
Sulfur	--	0.030
Chromium	14.00	16.00
Nickel	6.00	7.00
Molybdenum	0.50	1.00
Columbium (Niobium)	8 x C	0.75
Copper	1.25	1.75

3.1.1 Check Analysis

Composition variations shall meet the applicable requirements of AMS2248.

3.2 Condition

The product shall be supplied in the following condition:

3.2.1 Bars, Wire, Mechanical Tubing, Forgings, and Flash Welded Rings

Solution heat treated.

3.2.1.1 Bars

3.2.1.1.1 Rounds

Solution heat treated and centerless ground.

3.2.1.1.2 Squares, Hexagons, and Flats

Hot finished, solution heat treated, and descaled, or solution heat treated cold drawn, and descaled.

3.2.1.2 Wire

Solution heat treated and cold drawn.

3.2.1.3 Mechanical Tubing

Cold finished and solution heat treated.

3.2.1.4 Flash Welded Rings

Shall not be supplied unless specified or permitted on purchaser's part drawing. When supplied, they shall be manufactured in accordance with AMS7490.

3.2.2 Stock for Forging or Flash Welded Rings

As ordered by the forging or flash welded ring manufacturer.

3.3 Heat Treatment

Bars, wire, forgings, mechanical tubing, and flash welded rings shall be solution heat treated by heating to $1900^{\circ}\text{F} \pm 25$ ($1040^{\circ}\text{C} \pm 15$), holding at heat for not less than 1 hour, and cooling rapidly. Pyrometry shall be in accordance with AMS2750.

3.4 Properties

The product shall conform to the following requirements; hardness and tensile testing shall be conducted in accordance with ASTM A 370:

3.4.1 Bars, Wire, Forgings, Mechanical Tubing, and Flash Welded Rings

Shall be as follows on product 8.0 inch (200 mm) and under in least nominal cross-sectional dimensions.

3.4.1.1 As Solution Treated

3.4.1.1.1 Tensile Properties

Shall meet the requirements shown in Table 2 and 3.4.1.1.1.2.

3.4.1.1.1.1 Bars, Forgings, Tubing, and Flash Welded Rings

TABLE 2 - MINIMUM TENSILE PROPERTIES

Property	Value
Tensile Strength	125 ksi (860 MPa)
Yield Strength at 0.2% Offset	95 ksi (655 MPa)
Elongation in 4D	10%
Reduction of Area	40%

3.4.1.1.1.2 Wire

Not higher than 165.0 ksi (1135 MPa) or equivalent hardness (See 8.2).

3.4.1.1.2 Hardness

Shall be as follows:

3.4.1.1.2.1 Bars

Not higher than 311 HB, or equivalent (See 8.3), determined midway between surface and center.

3.4.1.1.2.2 Tubing, Flash Welded Rings, and Forgings

Not higher than 311 HB, or equivalent (See 8.3).

3.4.1.2 After Precipitation Heat Treatment

The product shall have the following properties after being precipitation heat treated by heating to $900^{\circ}\text{F} \pm 15$ ($480^{\circ}\text{C} \pm 8$), holding at heat for not less than 4 hours, and cooling in air:

3.4.1.2.1 Tensile Properties

Shall be as shown in Table 3:

TABLE 3 - MINIMUM TENSILE PROPERTIES	
Property	Value
Tensile Strength	180 ksi (1240 MPa)
Yield Strength at 0.2% Offset	170 ksi (1170 MPa)
Elongation in 4D	10%
Reduction of Area	40%

3.4.1.2.2 Hardness

Shall be not lower than 363 HB, or equivalent (See 8.3), but the product shall not be rejected on the basis of hardness if the tensile properties of 3.4.1.2.1 are acceptable, determined on specimens taken from the same sample as that with nonconforming hardness, or from another sample with similar nonconforming hardness.

3.4.2 Forging Stock

When a sample of stock is forged to a test coupon and heat treated as in 3.3 and 3.4.1.2, specimens taken from the heat treated coupon shall conform to the requirements of 3.4.1.2.1 and 3.4.1.2.2. If specimens taken from the stock after heat treatment as in 3.3 and 3.4.1.2 conform to the requirements of 3.4.1.2.1 and 3.4.1.2.2, the tests shall be accepted as equivalent to tests of a forged coupon.

3.4.3 Stock for Flash Welded Rings

Specimens taken from the stock after heat treatment as in 3.3 and 3.4.1.2 shall conform to the requirements of 3.4.1.2.1 and 3.4.1.2.2.

3.5 Quality

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5.1 When specified, steel shall conform to AMS2303.

3.5.2 Forgings shall have substantially uniform macrostructure. Standards for acceptance may be agreed upon by purchaser and vendor.

3.5.3 Grain flow of die forgings, except in areas which contain flash-line end grain, shall follow the general contour of the forgings, showing no evidence of reentrant flow.

3.6 Tolerances

Shall be as follows:

3.6.1 Bars and Wire

In accordance with AMS2241.

3.6.2 Mechanical Tubing

In accordance with AMS2243.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

The following are acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Composition (3.1) of each heat.

4.2.1.2 Tensile properties (3.4.1.1) and hardness (3.4.1.1.2) of each lot of bars, wire, forgings, mechanical tubing, and flash welded rings as solution heat treated.

4.2.1.3 Macrostructure of forgings (3.5.2).

4.2.1.4 Tolerances (3.6) of bars, wire, and mechanical tubing.

4.2.2 Periodic Tests

The following are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser:

4.2.2.1 Tensile properties (3.4.1.2.1) and hardness (3.4.1.2.2) of each lot of bars, wire, forgings, mechanical tubing, and flash welded rings after precipitation heat treatment, and grain flow of die forgings (3.5.3).

4.2.2.2 Ability of forging stock (3.4.2) and stock for flash welded rings (3.4.3) to develop required properties.

4.3 Sampling and Testing

Shall be as follows:

4.3.1 Bars, Wire, Mechanical Tubing, Flash Welded Rings, Forging Stock, and Stock for Flash Welded Rings

In accordance with AMS2371.

4.3.2 Forgings

In accordance with AMS2374.

4.4 Reports

The vendor of bars, wire, forgings, mechanical tubing, and flash welded rings shall furnish with each shipment a report showing the results of tests for composition of each heat and for tensile properties and hardness of each lot, and stating the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS5763D, product form, size, and quantity. If forgings are supplied, statement of compliance with the uniform macrostructure requirement (if agreed upon) and the size and melt source of stock used to make the forgings shall also be included.